

C688 (CuZn23Al3.5Co)

Standard Designation

EN not standardized /UNS C68800

Chemical Composition

Cu	Zn [%]	Al [%]	Co [%]
Balance	23	3.5	0.4

Description / Applications

C688 belongs to the copper zinc alloys with additional elements. C688 features an extremely high strength and a good bend formability.

Applications: connectors, IDC contacts

Physical Properties¹⁾

Density	8.2 g/cm ³	Thermal expansion coefficient	18.2·10 ⁻⁶ /K
Electrical conductivity	10.4 m/Ω·mm ² = 18 %IACS ²⁾	Modulus of elasticity	115 GPa ³⁾
Thermal conductivity	81 W/m·K		

¹⁾ Guideline values for soft temper, measured at room temperature

³⁾ 1 GPa = 1 kN/mm²

²⁾ IACS = International Annealed Copper Standard

Processing information

Weldability	Stress corrosion cracking
Solderability	

Mechanical properties

Temper	Tensile Strength Rm [MPa]	Yield Strength Rp0,2 [MPa]	Elongation A50 [%]	Hardness HV	Bendability ¹⁾			
					90° r/t ²⁾		180° r/t ²⁾	
					GW ³⁾	BW ⁴⁾	GW ³⁾	BW ⁴⁾
R530	530-600	min. 305	min. 30	150-180	0	0	0	0
R600	600-695	min. 435	min. 10	180-220	0	0.5	0.5	1
R670	670-770	min. 565	min. 3	190-230	0.5	2	1.5	2.5
R730	730-825	min. 655	min. 2	200-240	1	2	1.5	4
R780	780-875	min. 705	min. 2	210-250	2	-	2.5	-
R850	850-915	min. 765	min. 1	220-260	1.8	-	3	-
R895	min. 895	min. 805	min. 1	min. 235	-	-	-	-

¹⁾ The r/t values are valid for a strip thickness up to 0.6 mm (without crack). The data refer to rolled-to-temper material and a width of the bending area of 5 mm.

V-shape bend test according to ISO 7438

²⁾ r = inner radius, t = thickness

³⁾ GW = good way

⁴⁾ BW = bad way

The details in this datasheet are exclusively meant for general information only. They correspond to the state of knowledge at the time of issue and cannot replace the examination by our customers. Liability cannot be derived from the information.

Rev.: 01/2022

www.kemper-olpe.de