

# KHP<sup>®</sup> 102 (CuNiSi)

## Standard Designation

EN not standardised /UNS C19010

## Chemical Composition

Cu	Ni [%]	Si [%]	P [%]
Balance	1.3	0.25	0.03

## Description / Applications

KHP<sup>®</sup>102 is a CuNiSi (Corson type) alloy. KHP<sup>®</sup>102 provides an outstanding combination of high electrical conductivity and good strength.

Applications: connector springs, tabs, contact springs, switches, relays, leadframes

## Physical Properties<sup>1)</sup>

Density	8,9 g/cm <sup>3</sup>	Thermal expansion coefficient	16,8·10 <sup>-6</sup> /K
Electrical conductivity	35 (29 <sup>2)</sup> ) m/Ω·mm <sup>2</sup> 60 (50 <sup>2)</sup> )% IACS <sup>3)</sup>	Modulus of elasticity	127 GPa <sup>4)</sup>
Thermal conductivity	260 (197 <sup>2)</sup> ) W/m·K		

<sup>1)</sup> Guideline values for soft temper, measured at room temperature

<sup>2)</sup> for temper R580

<sup>3)</sup> IACS = International Annealed Copper Standard

<sup>4)</sup> 1 GPa = 1 kN/mm<sup>2</sup>

## Processing information

Weldability	good	Stress corrosion cracking	none
Solderability	good		

## Mechanical properties

Temper	Tensile Strength Rm [MPa]	Yield Strength Rp0,2 [MPa]	Elongation A50 [%]	Hardness HV	Bendability <sup>1)</sup>			
					90° r/t <sup>2)</sup>		180° r/t <sup>2)</sup>	
					GW <sup>3)</sup>	BW <sup>4)</sup>	GW <sup>3)</sup>	BW <sup>4)</sup>
R360	360 - 430	min. 250	min. 12	100 - 130	0	0	0	0
R410	410 - 480	min. 360	min. 10	130 - 150	0	0	0,5	1
R460	460 - 530	min. 430	min. 8	140 - 160	1	1	1	1
R520	520 - 580	min. 490	min. 5	150 - 170	1	1,5	1,5	2
R580	580 - 650	min. 540	min. 9	175 - 205	0,5	1	1	1,5

<sup>1)</sup> The r/t values are valid for a strip thickness up to 0.6 mm (without crack). The data refer to rolled-to-temper material and a width of the bending area of 5 mm.

V-shape bend test according to ISO 7438

<sup>2)</sup> r = inner radius, t = thickness

<sup>3)</sup> GW = good way

<sup>4)</sup> BW = bad way

The details in this datasheet are exclusively meant for general information only. They correspond to the state of knowledge at the time of issue and cannot replace the examination by our customers. Liability cannot be derived from the information.

Rev.: 07/2020

[www.kemper-olpe.de](http://www.kemper-olpe.de)