



## CuSn5

## Standard designation

EN	CW451K	UNS Alloy-No.	C51000
----	--------	---------------	--------

## Chemical composition

Cu	Sn [%]	P [%]	
Balance	4,5 - 5,5	0.01 - 0.4	

## Applications

Components for the electronic industry, Connector springs, relays, leaf springs, switches, parts in the machine and apparatus construction

Physical Properties<sup>1)</sup>

Density	8.85 g/cm <sup>3</sup>	Thermal expansion coefficient	18.2·10 <sup>-6</sup> /K
Electrical conductivity	10 m/Ω·mm <sup>2</sup> 16,5 % IACS <sup>2)</sup>	Modulus of elasticity	118 GPa <sup>3)</sup>
Thermal conductivity	82 W/m·K		

<sup>1)</sup> Guideline values for soft temper, measured at room temperature

<sup>3)</sup> 1 GPa = 1 kN/mm<sup>2</sup>

<sup>2)</sup> IACS = International Annealed Copper Standard

## Processing information

Weldability	good	Stress corrosion cracking	none
Solderability	very good		

## Mechanical properties

Temper	Tensile strength Rm [MPa]	Yield strength Rp0,2 [MPa]	Elongation A50 [%]	Hardness HV	Bendability <sup>1)</sup>			
					90° r/t <sup>2)</sup>		180° r/t <sup>2)</sup>	
					GW <sup>3)</sup>	BW <sup>4)</sup>	GW <sup>3)</sup>	BW <sup>4)</sup>
R310/H75	310 - 390	max. 250	min. 45	75 - 105	0	0	0	0
R400/H120	400 - 500	min. 240	min. 14	120 - 160	0	0	0	0
R490/H160	490 - 580	min. 430	min. 8	160 - 190	0	0	0	0.5
R550/H180	550 - 640	min. 510	min. 4	180 - 210	0	0	0.5	1
R630/H200	630 - 720	min. 600	min. 2	200 - 230	0	1.5	1	2
R690/H220	min. 690	min. 670	-	min. 220	1	3	1	5

<sup>1)</sup> The r/t values are valid for a strip thickness up to 0.6 mm (without crack). The data refer to rolled-to-temper material and a width of the bending area of 5 mm.

<sup>2)</sup> r = inner radius, t = thickness

<sup>3)</sup> GW = good way

<sup>4)</sup> BW = bad way

The details in this datasheet are exclusively meant for general information only. They correspond to the state of knowledge at the time of issue and cannot replace the examination by our customers. Liability cannot be derived from the information.

Rev.: 02/2012

[www.kemper-olpe.de](http://www.kemper-olpe.de)